SKZ LABORATORY PESHAWAR
ANALYSIS REPORT

SAMPLE PARTICULARS

Commodity: Talc Mesh Powder
Sampling Place: SKZ Yard Peshawar
Material Name: Agam 02
Packing: 25 kg bag / Ton bag
Mesh: Above 325 (Bettersizer ST Particle Analysis)

CHEMICAL REPORTS

Sno	Parameters	Method	Unit	Test Result
01	Loss on Ignition (L.O.I)	In House (Gravimetric) 1000^{o}C	%	**Under 8**
02	Silica as (SiO_2)	Based on Scott (Gravimetric)	%	**60% - 64%**
03	Magnesium as MgO	Based on Scott (Titrimetric)	%	**30% - 33%**

PHYSCAL REPORT

Sno	Parameters	Method	Test Result
01	Whiteness	`Konica color reader	**Above 93**
02	Sieve residue	Sa per A S T M E	**0.03**
03	Bulk density (gms/cm3)		**0.31**

